

## Application Note

### /// Viscosity measurement of calcium and magnesium phosphate

---

#### PRODUCT

ROTAVISC hi-vi I Complete (0025000312)  
labworldsoft® 6 Visc (0020101872)

---

#### INDUSTRY

Chemical

---

#### TASK / OVERVIEW

The requirement was to measure the viscosity trend of calcium and magnesium phosphate at an increasing speed of 6 to 20 rpm. The sample was stirred and thereby homogenized at a room temperature of 23.5 °C. Subsequently, its viscosity was measured with ROTAVISC hi-vi I and the spindle SP 9.

---

#### EXPERIMENTAL SETUP

Viscometer	ROTAVISC hi-vi I
Spindle	SP 9
Medium	Calcium and magnesium phosphate
Sample vessel	Customer's vessel
Speed	6 – 20 rpm
Sample temperature	23.5 °C

---

#### SAMPLE MATERIAL

Calcium- and magnesium phosphate (39 %) in glycerol




**SAMPLE PREPARATION**

The sample was homogenized by stirring prior to the measurement.

**RESULT**

Speed	Viscosity
6 rpm	7,000 mPas
8 rpm	7,700 mPas
10 rpm	8,520 mPas
12 rpm	9,433 mPas
14 rpm	10,486 mPas
18 rpm	13,000 mPas
20 rpm	14,220 mPas

The results show a shear-thickening behaviour of the sample.



**000 «Диаэм»**

**С.-Петербург**  
+7 (812) 372-6040  
spb@dia-m.ru

**Казань**  
+7(843) 210-2080  
kazan@dia-m.ru

**Новосибирск**  
+7(383) 328-0048  
nsk@dia-m.ru

**Ростов-на-Дону**  
+7 (863) 303-5500  
rnd@dia-m.ru

**Воронеж**  
+7 (473) 232-4412  
vrn@dia-m.ru

**Екатеринбург**  
+7 (912) 658-7606  
ekb@dia-m.ru

**Москва**  
ул. Магаданская, д. 7, к. 3 ■ тел./факс: (495) 745-0508 ■ sales@dia-m.ru

**Йошкар-Ола**  
+7 (927) 880-3676  
nba@dia-m.ru

**Кемерово**  
+7 (923) 158-6753  
kemerovo@dia-m.ru

**Красноярск**  
+7(923) 303-0152  
krsk@dia-m.ru

**Армения**  
+7 (094) 01-0173  
armenia@dia-m.ru

**www.dia-m.ru**

